ASPHALTAN B

Technical Data Sheet

Issue 01/2022

Delivery specifications

- **Pastilles** **0 – 2 mm: at least 95 %**

Field of application

- **Quantities of use: 2 - 3 % by wt. (related to the bitumen content)**

Packaging

- **PE-bags on pallets enveloped with PE shrink film**
- **Big Bag**

Product Specification

Characteristic	ROMONTA test method	Specification limits
Solidification point	W 1.1	95 – 105 °C
Dropping point	W 1.3.2	110 – 120 °C
Viscosity at 120 °C	W 7.1.1	10 – 200 mPas

The present information sheet supersedes all previous issues.

The preceding information is based on the state of our present knowledge and on careful investigations and is merely meant to describe the product. We reserve the right to make modifications to this leaflet.
In submitting this information, no liability is assumed with respect to certain properties and applications as well as for the observance of any third parties' rights.

ROMONTA Holding GmbH
OT Amsdorf · Chausseestraße 1
D-06317 Seegebiet Mansfelder Land
Germany

www.romonta.de
E-Mail: marketing@romonta.de

ROMONTA
wax and more