# ROMONTA N

## Technical Data Sheet

**Issue 04/2024**

### Delivery specifications

- **Granular material G1600** **0.16 - 2.0 mm: at least 95 %**

### Packaging

- **25 kg PE bags on pallets of 750 kg, 1000 kg or 1250 kg each, enveloped with PE shrink film**
- **5 kg PE bags in paltainers of 450 kg each**
- **Big Bag**

### Product Specification

| Characteristic | ROMONTA test method | Specification limits |
|---|---|---|
| Solidification point | W 1.1 | 75 - 80 °C |
| Acid value | W 2.1.1 | 22 - 36 mg KOH/g |
| Saponification value | W 2.2.1 | 75 - 100 mg KOH/g |
| Residue on ignition | W 6.1.1 | not more than 0.5 % by wt. |

**The present information sheet supersedes all previous issues.**

**The preceding information is based on the state of our present knowledge and on careful investigations and is merely meant to describe the product. We reserve the right to make modifications to this leaflet.**
**In submitting this information, no liability is assumed with respect to certain properties and applications as well as for the observance of any third parties' rights.**

**ROMONTA Holding GmbH**
OT Amsdorf · Chausseestraße 1
D-06317 Seegebiet Mansfelder Land
Germany

www.romonta.de
E-Mail: marketing@romonta.de

ROMONTA
wax and more